

## Mini box type 1

Thin-wall heat shrink tubing / flexible / flame retardant / 2:1 / H-2(Z)

### Features:

- Crosslinked Polyolefin
- Shrink ratio: 2:1
- Flame retardant
- General purpose
- High flexibility
- UV resistant (according to ISO 8580 test report)

### Approvals:

- UL224 125 °C VW-1 600 V file E204071
- CSA file no.: 1934614
- Meets: RoHS, Sony-SS-00259

### Application:

- Operating temperature: -55 °C to +125 °C
- Minimum shrink temperature: +70 °C
- Minimum full recovery temperature: +100 °C
- Longitudinal change: 0 ± 10% max.

### Order information:

- Colors: black, red, blue, yellow, green, white, purple, brown



| Type / Size      | As supplied:<br>inside diameter in mm<br>(min.) | After recovery:<br>inside diameter in mm<br>(max.) | After recovery:<br>wall thickness in mm<br>(min.) | Box / Meter |
|------------------|-------------------------------------------------|----------------------------------------------------|---------------------------------------------------|-------------|
| H-2(Z) 1,2/0,6   | 1,2                                             | 0,6                                                | 0,33                                              | 10          |
| H-2(Z) 1,6/0,8   | 1,6                                             | 0,8                                                | 0,36                                              | 10          |
| H-2(Z) 2,4/1,2   | 2,4                                             | 1,2                                                | 0,44                                              | 10          |
| H-2(Z) 3,2/1,6   | 3,2                                             | 1,6                                                | 0,44                                              | 10          |
| H-2(Z) 4,8/2,4   | 4,8                                             | 2,4                                                | 0,51                                              | 10          |
| H-2(Z) 6,4/3,2   | 6,4                                             | 3,2                                                | 0,56                                              | 5           |
| H-2(Z) 9,5/4,8   | 9,5                                             | 4,8                                                | 0,56                                              | 5           |
| H-2(Z) 12,7/6,4  | 12,7                                            | 6,4                                                | 0,65                                              | 5           |
| H-2(Z) 16,0/8,0  | 16,0                                            | 8,0                                                | 0,69                                              | 5           |
| H-2(Z) 19,0/9,5  | 19,0                                            | 9,5                                                | 0,80                                              | 5           |
| H-2(Z) 25,4/12,7 | 25,4                                            | 12,7                                               | 0,90                                              | 5           |